

# **Product Data Sheet**

## **Gulfcrown® EP Grease**

#### Multi-purpose extreme pressure lithium grease

Premium quality, extreme-pressure lithium soap thickened grease designed to perform in a wide variety of applications requiring grease with extreme pressure properties and good load-carrying capacity.

#### **Features and Benefits**

- Longer equipment life
- Excellent protection against wear
- NLGI LB certified (NLGI #2 only)

- Outstanding oxidation resistance
- Superior rust and corrosion protection
- Operates at low to moderate speeds

#### **Applications**

- Multi-purpose grease applications
- Automotive chassis
- Fan bearings, pump bearings

- Earthmoving equipment, farming, mining
- Plain and antifriction bearings
- Construction equipment

**NLGI grade 000** is a semifluid that is red in color and has a smooth texture. **Gulfcrown EP 000** is a premium quality grease containing extreme pressure, anti-wear, and anti-rust additives. It is often recommended for use in centralized lubrication systems, underground mining equipment and enclosed gear cases where leaking gear boxes have lost their ability to retain standard gear oil.

### Typical Properties

| NLGI Grade<br>Product Code       | Test Method | #2<br>343307  | #000<br>343303 |
|----------------------------------|-------------|---------------|----------------|
| Thickener Type                   | ASTM D-128  | Lithium 12-OH | Lithium 12-OH  |
| Color                            |             | Dark Brown    | Red            |
| Texture                          |             | Smooth        | Smooth         |
| Worked Penetration               | ASTM D217   | 265-295       | 445-475        |
| Base Oil Viscosity, cSt @ 40°C   | ASTM D-445  | 180           | 340            |
| Dropping Point, °F (°C) (min)    | ASTM D-2265 | 380 (193)     | -              |
| Four-Ball Wear Test, mm          | ASTM D-2266 | 0.52          | 0.55 max.      |
| Four-Ball Weld Point, kgf        | ASTM D-2596 | 250           | 315            |
| Water Washout, wt.% loss @ 175°F | ASTM D-1264 | 3.5           | -              |
| Copper Strip Corrosion           | ASTM D-4048 | 1b            | 1b             |
| Rust Prevention, rating          | ASTM D-1743 | Pass          | Pass           |
| Timken OK Load, Ibs. (min)       | ASTM D-2509 | 45            | 40 min         |

These properties are typical of current production, minor variations are to be expected in normal manufacturing.

(∰)

Rev. 02/24





